

START DATE 16/05/2022
END DATE 23/05/2022

APPLICANT

RESIN PRO SRL
Via XXV Aprile Z.I. Snc
19021 Arcola SP

SAMPLE DESCRIPTION Quotation No. 1203/DB
Receiving Date: 16/05/2022
Quantity: 1 bottle
Name: NATURESIN
Sample Return No
Buyer's Name: RESIN PRO SRL

Sample 01 SAMPLE DESCRIPTION: WHITE POWDER (NATURESIN)

Test	Rating	Failure result
Specification for Migration of Certain Elements EN 71-3: 2019 + A1:2021	P	
Polycyclic aromatic hydrocarbons (PAH) content by solvent extraction and determined by Gas Chromatographic - Mass Spectrometry (GC/MS) REACH Regulation (EC) no. 1907/2006 & amendment (EU) no. 1272/2013 Annex XVII Item 50	P	
8028 - Phthalate plasticizers content EN 14372:2005 Reg. (EC) 1907/2006 REACH annex XVII Items 51 (& 52 if applicable)	P	
8051 - SCCPSs Short chain chlorinated paraffins C10-C13	P	
INTERTEK IHTM Based on ISO 18219:2015Reg. (EU) 2019/1021 (POP)		
Organotin Content by Tin Screening CPSC-CH-E1003-09 (modified) Reg. (EC) 1907/2006 REACH annex XVII Item 20	P	
Cadmium Content CPSC-CH-E1003-08.1 Reg. (EC) 1907/2006 REACH annex XVII Item 23	P	

P = MEETS REQUIREMENT / A = ACCEPTABLE / F = DOES NOT MEET REQUIREMENT / NR = NO REQUIREMENT / SC = STILL CONTINUES / X = NOT PERFORMED
Values in brackets represent the limits



LAB N° 0579 L

TEST METHOD	SAMPLE DESCRIPTION	PARAMETERS	RESULT	U.M.	LIMITS	LQ	NOTES	LAB		
Specification for Migration of Certain Elements EN 71-3: 2019 + A1:2021	01 SAMPLE DESCRIPTION: WHITE POWDER (NATURESIN)	EN 71-3:2019 + A1:2021 - Category 1 (dry, brittle, powder like or pliable material)	Alluminium	< 5	mg/kg	2250	5		ITA	
			7429-90-5							
			Antimony	< 1	mg/kg	45	1			ITA
			7440-36-0							
			Arsenic	< 0,2	mg/kg	3,8	0,2			ITA
			7440-38-2							
			Barium	< 5	mg/kg	1500	5			ITA
			7440-39-3							
			Boron	< 5	mg/kg	1200	5			ITA
			7440-42-8							
			Cadmium	< 0,1	mg/kg	1,3	0,1			ITA
			7440-43-9							
			Chromium III	< 1	mg/kg	37,5	1			ITA
			16065-83-1							
			Chromium VI	< 0,02	mg/kg	0,02	0,02	*		ITA
			18540-29-9							
			Cobalt	< 1	mg/kg	10,5	1			ITA
			7440-48-4							
			Copper	< 5	mg/kg	622,5	5			ITA
			7440-50-8							
Lead	< 0,2	mg/kg	2,0	0,2			ITA			
7439-92-1										
Manganese	< 5	mg/kg	1200	5			ITA			
7439-96-5										
Mercury	< 0,5	mg/kg	7,5	0,5			ITA			
7439-97-6										
Nickel	< 5	mg/kg	75	5			ITA			
7440-02-0										
Selenium	< 1	mg/kg	37,5	1			ITA			
7782-49-2										
Strontium	617	mg/kg	4500	5			ITA			
7440-24-6										
Tin	< 0,2	mg/kg	15000	0,2			ITA			
7440-31-5										
Zinc	< 5	mg/kg	3750	5			ITA			
7440-66-6										
Organic Tin	< 0,5	mg/kg	0,9	0,5	#tin	*	ITA			
Polycyclic aromatic hydrocarbons (PAH) content by solvent extraction and determined by Gas Chromatographic - Mass Spectrometry (GC/MS) REACH Regulation (EC) no. 1907/2006 & amendment (EU) no. 1272/2013 Annex XVII Item 50	01 SAMPLE DESCRIPTION: WHITE POWDER (NATURESIN)		Benzo[a]pyrene	< 0,1	mg/kg	0,5	0,1	*	ITA	
			50-32-8							
			Benzo[e]pyrene	< 0,1	mg/kg	0,5	0,1	*	ITA	
192-97-2										



LAB N° 0579 L



TEST METHOD	SAMPLE DESCRIPTION	PARAMETERS	RESULT	U.M.	LIMITS	LQ	NOTES	LAB
		Benzo[a]anthracene 56-55-3	< 0,1	mg/kg	0,5	0,1	*	ITA
		Chrysene 218-01-9	< 0,1	mg/kg	0,5	0,1	*	ITA
		Benzo[b]fluoranthene 205-99-2	< 0,1	mg/kg	0,5	0,1	*	ITA
		Benzo[j]fluoranthene 205-82-3	< 0,1	mg/kg	0,5	0,1	*	ITA
		Benzo[k]fluoranthene 207-08-9	< 0,1	mg/kg	0,5	0,1	*	ITA
		Dibenzo[a,h]anthracene 53-70-3	< 0,1	mg/kg	0,5	0,1	*	ITA
8028 - Phthalate plasticizers content EN 14372:2005 Reg. (EC) 1907/2006 REACH annex XVII Items 51 (& 52 if applicable)	01 SAMPLE DESCRIPTION: WHITE POWDER (NATURESIN)	DBP-Di-butyl phthalate 84-74-2	< 0,003	%	0,1	0,003	11	ITA
		BBP-Butyl benzyl phthalate 85-68-7	< 0,003	%	0,1	0,003	11	ITA
		DEHP-Di-(2-ethylhexyl) phthalate 117-81-7	< 0,003	%	0,1	0,003	11	ITA
		DIBP-Di-(Iso-Butyl) Phthalate 84-69-5	< 0,003	%	0,1	0,003	11 *	ITA
		DNOP-Di-n-octyl phthalate 117-84-0	< 0,003	%	0,1	0,003	11	ITA
		DINP-Di-isononyl phthalate 28553-12-0	< 0,003	%	0,1	0,003	11	ITA
		DIDP-Di-isodecyl phthalate 26761-40-0	< 0,003	%	0,1	0,003	11	ITA
		DEHP+DBP+BBP+DIBP	N.R.	%	0,1 ⁽¹⁾		11 *	ITA
		DNOP + DINP+ DIDP	N.R.	%	0,1 ⁽²⁾		11 *	ITA



LAB N° 0579 L

Intertek Italia S.p.a.
 Administrative Office Via Miglioli, 2/A - 20063 Cernusco Sul Naviglio (MI)
 Operational Office Via di Stagno 17 F/G - 50055 Lastra a Signa (FI)
 Tel. 0039055790873 Fax 0039055791198




Validated by: Giovanni Servadei

TEST METHOD	SAMPLE DESCRIPTION	PARAMETERS	RESULT	U.M.	LIMITS	LQ	NOTES	LAB
8051 - SCCPs Short chain chlorinated paraffins C10-C13 INTERTEK IHTM Based on ISO 18219:2015Reg. (EU) 2019/1021 (POP) <u>Operating Conditions.</u> By High Performance Liquid Chromatography&Mass Spectroscopy (LC-MS-MS) Analysis	01 SAMPLE DESCRIPTION: WHITE POWDER (NATURESIN)	Short-chained chlorinated paraffins (C10-C13)	< 0,01	% (w/w)	0,15	0,01	*	ITA




LAB N° 0579 L

Laboratory Manager



Ilenia Francioni

ilenia.francioni@intertek.com


Dott. Luca Di Monte
 Ordine dei Chimici e dei Fisici della Toscana
 Sez. A Chimico n°2323
luca.dimonte@intertek.com

Validated by: Giovanni Servadei

TEST METHOD	SAMPLE DESCRIPTION	PARAMETERS	RESULT	U.M.	LIMITS	LQ	NOTES	LAB
Organotin Content by Tin Screening CPSC-CH-E1003-09 (modified) Reg. (EC) 1907/2006 REACH annex XVII Item 20	01 SAMPLE DESCRIPTION: WHITE POWDER (NATURESIN)	Tin 7440-31-5	< 0,002	%	0,1	0,002	*	ITA
Cadmium Content CPSC-CH-E1003-08.1 Reg. (EC) 1907/2006 REACH annex XVII Item 23	01 SAMPLE DESCRIPTION: WHITE POWDER (NATURESIN)	Cadmium 7440-43-9	< 0,00025	%	0,1 ⁽³⁾	0,00025	*	ITA

References

⁽¹⁾ PHTHALATES CONTENT REQUIREMENT IN ANNEX XVII ITEM 51 OF THE REACH REGULATION (EC) NO. 1907/2006

⁽²⁾ PHTHALATES CONTENT REQUIREMENT IN ANNEX XVII ITEM 52 OF THE REACH REGULATION (EC) NO. 1907/2006

⁽³⁾ CADMIUM CONTENT REQUIREMENT IN ANNEX XVII ITEM 23 OF THE REACH REGULATION (EC) NO. 1907/2006 (FORMERLY KNOWN AS DIRECTIVE 91/338/EEC)

Test performed by:

ITA: Intertek Italia S.p.a.

Via di Stagno 17 F/G

50055 Lastra a Signa (FI)

Tests marked with star (*) haven't been Accredia accredited.

Notes

#tin = Organotin result is calculated using a 2,44 times factor based on the Tin result.

" = The result expressed as "%" is to be intended as weight of analyte on the weight of the sample.



LAB N° 0579 L

Laboratory Manager

 Ilenia Francioni
ilenia.francioni@intertek.com

Chemical Lab Manager

 Dott. Luca Dimonte
 Ordine dei Chimici e dei Fisici della Toscana
 Sez. A Chimico n°2323
luca.dimonte@intertek.com

START DATE 16/05/2022
 END DATE 23/05/2022

The partial reproduction of the present Test Report is not allowed without written authorization of the General Manager.
 The content of the present document refers exclusively to the submitted samples and not to the batch that they want to represent.
 A representative portion of the sample is kept for 60 days. Specimen are kept for 30 days.
 Sample are drawn by customer. As received by the customer, the sample was accepted for testing. The sample description is based only on customer declaration/information.
 Limits are based on Customer's Manual in force available at Intertek Italia S.p.A. - Via di Stagno, 17 F/G - 50055 Lastra a Signa (FI)
 Uncertainty is the extended uncertainty calculated using a coverage factor of 2 which gives a level of confidence of approximately 95%.
 All the results are reported without considering the uncertainty.
 This test report shows the logo of Intertek Italia Spa, as the testing laboratory that performed the tests. The possible presence of other logos is due to the explicit request of the customer to have their own logo on the test report.

UM:Unit of Measurement
 LQ:Quantification Limit

RESULTS MARKED IN RED EXCEED LIMITS

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct.



LAB N° 0579 L

Intertek Italia S.p.a.
 Administrative Office Via Miglioli, 2/A - 20063 Cernusco Sul Naviglio (MI)
 Operational Office Via di Stagno 17 F/G - 50055 Lastra a Signa (FI)
 Tel. 0039055790873 Fax 0039055791198

Laboratory Manager

 Ilenia Francioni
ilenia.francioni@intertek.com

Chemical Lab Manager

 Dott. Luca Di Monte
 Ordine dei Chimici e dei Fisici della Toscana
 Sez. A Chimico n°2323
luca.dimonte@intertek.com

Validated by: Giovanni Servadei



LAB N° 0579 L

Laboratory Manager
Ilania Francioni
Ilania Francioni
ilania.francioni@intertek.com

Chemical Lab Manager
Dott. Luca Di Monte
Luca Di Monte
Luca Di Monte
Sez. A Chimico n°2323
luca.dimonte@intertek.com

Stampa circolare: ORDINE DEI CHIMICI E DEI FISICI DELLA TOSCANA, Sez. A Chimico n°2323



END OF TEST REPORT



LAB N° 0579 L

Laboratory Manager
Ilania Francioni
Ilania Francioni
ilania.francioni@intertek.com

Chemical Lab Manager
Dott. Luca Di Monte
Luca Di Monte
Luca Di Monte
Ordine dei Chimici e dei Fisici della Toscana
Sez. A Chimico n°2323
luca.dimonte@intertek.com

Validated by: Giovanni Servadei